



## Technical Test Results for:

### Hollowrap 14mu Hand Stretch

TEST NO. L561/2014

**EMH40-300-14**

SAMPLE TESTED

**40 cm. x 300 m. x 14 mic.  
HAND GRADE**

PROPERTIES	UNIT	STANDARD	RESULT	ACCEPTANCE	METHOD
TENSILE STRENGTH (min)	(MD)	MPa	35	PASS	ASTM D 882
	(TD)		14	PASS	
LOAD AT BREAK (min)	(MD)	N	12	PASS	ASTM D 882
	(TD)		4	PASS	
ELONGATION AT BREAK (min)	(MD)	%	320	PASS	ASTM D 882
	(TD)		580	PASS	
TEAR RESISTANCE (min)	(MD)	mN	500	PASS	ASTM D 1922
	(TD)		2000	PASS	
PEEL CLING (min)		N-mm	5	PASS	ASTM D 5458
PUNCTURE (min)		N-mm	1100	PASS	ASTM D 5748
DART IMPACT (min)		g	40	PASS	ASTM D 1709
ULTIMATE STRETCH		%	200	PASS	HSTM
THICKNESS		Micron	14±1	PASS	DIAL GAUGE
WIDTH		cm	40±1	PASS	SCALE

INSPECTED BY

**SURIYAN NOCHAITASORN**

QC SPECIALIST

APPROVED BY

*Palid*

QC MANAGER