



Technical Test Results for:

Hollowrap 17mu Machine Stretch

TEST NO. L1117/2014

EHM50-1800-17

SAMPLE TESTED

50 cm. x 1800 m. x 17 mic.

MACHINE GRADE

PROPERTIES	UNIT	STANDARD	RESULT	ACCEPTANCE	METHOD
TENSILE STRENGTH (min)	(MD)	32	51	PASS	ASTM D 882
	(TD)	16	29	PASS	
LOAD AT BREAK (min)	(MD)	12	20	PASS	ASTM D 882
	(TD)	6	12	PASS	
ELONGATION AT BREAK (min)	(MD)	390	460	PASS	ASTM D 882
	(TD)	550	766	PASS	
TEAR RESISTANCE (min)	(MD)	1750	2901	PASS	ASTM D 1922
	(TD)	4200	6463	PASS	
PEEL CLING (min)	N-mm	5	11	PASS	ASTM D 5458
PUNCTURE (min)	N-mm	1500	2870	PASS	ASTM D 5748
ULTIMATE STRETCH	%	230	258	PASS	HSTM
THICKNESS	Micron	17±1	17	PASS	DIAL GAUGE
WIDTH	cm	50±1	50	PASS	SCALE

INSPECTED BY

SURIYAN NOCHAITASORN

QC SPECIALIST

APPROVED BY

Palid

QC MANAGER